

EXTERIOR FILM

ARCHITECTURAL WINDOW FILMS

PRODUCT	VISIBLE LIGHT TRANSMISSION	TOTAL SOLAR REFLECTANCE	TOTAL SOLAR ABSORBANCE	VISIBLE LIGHT REFLECTANCE	VISIBLE LIGHT REFLECTANCE INTERIOR	VISIBLE LIGHT REFLECTANCE EXTERIOR	EXTERIOR WINTER U-VALUE (EN 673 W/M²K)	UV REJECTED	GLARE REDUCTION	SHADING COEFFICIENT	SOLAR HEAT GAIN COEFFICIENT (G VALUE)	TOTAL SOLAR ENERGY REJECTED
Specialty Products												
4M CLEAR EXT	86%	78%	9%	13%	9%	9%	6.19	99%	3%	0.95	0.81	19%

All data values above are representative and are provided for comparison purposes only.

INTERIOR FILM

ARCHITECTURAL WINDOW FILMS

PRODUCT	VISIBLE LIGHT TRANSMISSION	TOTAL SOLAR TRANSMISSION	TOTAL SOLAR REFLECTANCE	TOTAL SOLAR ABSORBANCE	VISIBLE LIGHT REFLECTANCE INTERIOR	VISIBLE LIGHT REFLECTANCE EXTERIOR	EXTERIOR WINTER U-VALUE (EN 673 W/M²K)	UV REJECTED	GLARE REDUCTION	SHADING COEFFICIENT	SOLAR HEAT GAIN COEFFICIENT (G VALUE)	IR REJECTED @ 980NM	TOTAL SOLAR ENERGY REJECTED
Specialty Products													
2M UVX	88%	75%	8%	17%	10%	10%	5.96	99.9%	5%	0.93	0.81		19%
2M WHITE MATTE	64%	58%	17%	25%	21%	21%	5.85	99%	28%	0.76	0.66		34%
DRMPS 7 ONE WAY MIRROR	7%	6%	53%	41%	14%	60%	5.17	99%	94%	0.18	0.16		84%
6M ANTI-GRAFFITI	86%	76%	10%	14%	10%	10%	6.19	95%	3%	0.93	0.81		19%
4M ANTI-GRAFFITI	86%	78%	9%	13%	9%	9%	6.19	95%	3%	0.93	0.81		19%

All data values above are representative and are provided for comparison purposes only.